



TBP Converting, Inc.
Dow Instant Glaze III PDS

Product Information

Silicone Adhesive Sealants

DOW CORNING

Dow Corning® Instant Glaze III Window Assembly Adhesive

FEATURES

- Instant green strength
- Exhibits silicone weather resistance (meets ASTM C 793 weather resistance)
- Low VOC
- Neutral cure
- Adheres to most common window substrates
- Open time up to 15 minutes
- Pot life up to 24 hours at 120°C
- Excellent clarity
- Service temperatures from -30 to 150°C (-23 to 300°F)
- Reduces silicone contamination and cleanup
- Easy to deglaze
- Can be used with high speed robots and pumps or standard XY glazing equipment

BENEFITS

- Instant green strength delivers improved productivity in window assembly
- Long open time, pot life and moderate application temperature (93 to 130°C [200 to 265°F]) offer a user-friendly application
- Unique physical properties minimize contamination of window components during assembly

COMPOSITION

- Neutral (moisture) cure, 100% silicone, hot-melt sealant

Neutral-cure hot-melt silicone for automated assembling of windows

APPLICATIONS

- *Dow Corning*® Instant Glaze III Window Assembly Adhesive is designed for use as productivity enhancer in the assembly of windows and doors. It is used with various types of high-speed automatic equipment (robots, XY tables, etc.) to improve manufacturing productivity and window performance. It can be used on most common window materials (wood, PVC, aluminum, fiberglass) without the need for any primer. *Dow Corning* Instant Glaze III Window Assembly Adhesive is also compatible with most common insulating glass sealants.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test ¹	Property	Unit	Result
CTM 0719	Viscosity at 120°C (248°F)	Pa sec	120
CTM 0044	Specific gravity, uncured		1.12
CTM 0243	Open time	minutes	15
CTM 0243	Green Strength at 15 minutes	MPa (psi)	0.03 (5)
CTM 0243	Green Strength at 60 minutes	MPa (psi)	0.04 (6)
ASTM C661	Durometer, Shore A	points	33
ASTM D412	Tensile strength	MPa (psi)	4.8 (700)
ASTM D412	Elongation	percent	949
ASTM D412	Modulus at 50% elongation	MPa (psi)	0.8 (122)
ASTM C719	Movement capability	percent	±50
ASTM C794	Peel strength		
	to float glass	kN/m (pli)	8.4 (46)
	to mill-finished aluminum	kN/m (pli)	10 (57)
	to PVC	kN/m (pli)	7.3 (40)
	to treated wood	kN/m (pli)	7.1 (39)
	to fiberglass	kN/m (pli)	10 (57)
	to Kynar-coated aluminum	kN/m (pli)	9.5 (53)
ASTM C793	Low-temperature flexibility	°C	-30
		°F	-23
ASTM C793	Weathering resistance		No cracks
ASTM C711	Service temperature range	°C	-30 to 150
		°F	-23 to 300

1. CTM: (Corporate Test Methods) correspond to standard ASTM tests in most instances.

Copies of CTMs are available upon request.

ASTM: American Society for Testing and Materials.

DESCRIPTION

Dow Corning Instant Glaze III Window Assembly Adhesive is a 100% silicone, neutral-cure adhesive formulated to meet the demanding requirements of high-speed manufacturing of windows and doors. *Dow Corning* Instant Glaze III Window Assembly Adhesive delivers instant green strength to offer productivity improvements in assembly applications. Windows made with *Dow Corning* Instant Glaze III Window Assembly Adhesive can be immediately handled and moved without the risk of compromising the integrity of the seal or distorting of the sash.

Dow Corning Instant Glaze III Window Assembly Adhesive is a clear transparent color formulation.

APPROVALS/ SPECIFICATIONS

AAMA 805.2-94, group A
ISO 11600 (25% mvt capability)
CTBA L114, Norm XP P23-310e

HOW TO USE

Preparation

Surfaces should be clean and dry before sealant application. No primers are needed with *Dow Corning* Instant Glaze III Window Assembly Adhesive.

Application

Dow Corning Instant Glaze III Window Assembly Adhesive is applied from 20 liter or 205kg drums with a platen-type hot-melt pump. Application temperature is typically 120°C (250°F). When the melt temperature has been reached, application with automated or hand-assisted glazing equipment can begin.

Once applied to the sash, the glass should be installed within 15 minutes. *Dow Corning* Instant Glaze III Window Assembly Adhesive can be applied on the sash or directly on the glass. Once applied, this product

reacts with atmospheric moisture to form a weather resistant, flexible silicone sealant. Exposure of opened containers with air should be minimized.

HANDLING PRECAUTIONS

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning Web site at dowcorning.com. You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

Material is applied at 120°C (250°F). Use common personal protective equipment to prevent contacting the hot material with skin or eyes.

USABLE LIFE AND STORAGE

When stored at or below 32°C (90°F) in the original unopened containers, this product has a usable life of 12 months from the date of manufacture. Refer to product packaging for "Use By Date."

PACKAGING INFORMATION

This product is available in 20 liter (18kg) pails and 200 liter (205kg) drums.

LIMITATIONS

This product is not intended for use:

- In spaces totally confined from atmospheric moisture during cure
- In continuous water immersion
- In below-grade applications
- In structural glazing applications
- As an insulating glass sealant
- On surfaces that require painting or staining
- On surface that might bleed oils, plasticizers or solvents
- On frost-laden or wet surfaces

Avoid prolonged exposure to citrus-containing cleaners, solvents and solvent-based cleaners.

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our Web site, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY
DISCLAIMS ANY OTHER
EXPRESS OR IMPLIED
WARRANTY OF FITNESS FOR A
PARTICULAR PURPOSE OR
MERCHANTABILITY.**

**DOW CORNING DISCLAIMS
LIABILITY FOR ANY
INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

We help you invent the future. TM

dowcorning.com