



TBP Converting, Inc.
Rogers Corporation
BISCO HT-6135 PDS

BISCO® HT-6135

BISCO® HT-6135 is a part of the performance grade solid silicone series. High tear strength and extremely tight thickness tolerances of these materials offer added benefits for sealing.

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
PHYSICAL			
Color	Visual	Cream	---
Thickness, mm (inches)	Internal	0.250 - 1.59 (0.010 - 0.063)	---
Specific Gravity, (g/cc)	Internal	1.22	---
Durometer, Shore A	ASTM D2240	33	35 ± 5
Compression Set, %	ASTM D395 150°C (302°F) / 70 hrs / 25%	< 25	---
Tensile Strength, MPa (psi)	ASTM D412	> 5.52 (> 800)	---
Elongation, %	ASTM D412	580	---
Tear Resistance, ppi	ASTM D624	116	---

Specification values in bold are tested on a batch basis.

Further industry specifications tested in tables below.

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
ELECTRIC			
Dielectric Strength, Volts/mil	ASTM D149	381	---
Dielectric Constant, 1 kHz	ASTM D150	2.95	---
Dissipation Factor, 1 kHz	ASTM D495	0.001	---
Dry Arc Resistance, Seconds	ASTM D495	145	---
Volume Resistivity, Ohm-cm	ASTM D257	10 ¹⁴	---



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO logo, and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2002, 2003, 2004, 2008, 2019, 2020 Rogers Corporation.

All rights reserved. 0320-PDF • Publication #180-092

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
THERMAL			
Temperature Range, °C (°F)	Internal	-55 to +200 (-67 to +392)	---
Thermal Conductivity, W/m °K	ASTM D518	0.31	---
Low Temperature Brittleness	ASTM D2137 -62°C (-80°F) / 3 min	Pass	---

Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
0.254 (0.010)	± 0.051 (± 0.002)
0.508 (0.020)	± 0.076 (± 0.003)
0.787 (0.031)	± 0.102 (± 0.004)
1.600 (0.063)	± 0.152 (± 0.006)

Tape (PSA) Width Tolerances

NOMINAL WIDTH	TOLERANCE
mm (inches)	mm (inches)
> 660 - 914 (> 26 - 36)	+ 25.4/- 0 (+ 1/- 0)

VALUE ADDED OFFERINGS

- Adhesive (PSA) lamination on ≥ 0.031"
- Slit material/tapes

Notes:

*Typical Value- Value is based on historical data. Please note the frequency of testing varies.

**Specification- Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values. Additional industry specifications are available as well. All other properties are based on industry standard guidelines.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO logo, and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2002, 2003, 2004, 2008, 2019, 2020 Rogers Corporation. All rights reserved. 0320-PDF • Publication #180-092