

TBP Converting, Inc. Rogers Corporation BISCO HT-6210 PDS



BISCO® HT-6210

BISCO® HT-6210 extra soft silicone material is part of the performance grade solid silicone series. The material's low Shore OO durometer, high tear strength, and extremely tight thickness tolerances offer added benefits for sealing.

Features & Benefits:

- Provides low closure force
- Bridges the gap between foams and high durometer solids

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
PHYSICAL			
Color	Visual	Gray	
Thickness, mm (inches)	Internal	0.250 - 3.18 (0.010 - 0.125)	
Specific Gravity, (g/cc)	Internal	1.07	
Durometer, Shore OO	ASTM D2240	61	62 ± 4
Compression Set, %	ASTM D395 150°C (302°F) / 22 hrs / 50%	< 25	
Tensile Strength, MPa (psi)	ASTM D412	3.3 (480)	> 1.4 (> 200)
Elongation, %	ASTM D412	565	> 400
Tear Resistance, ppi	ASTM D624	> 20	

Specification values in bold are tested on a batch basis.

Further industry specifications tested in tables below.

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
ELECTRIC			
Dielectric Strength, Volts/mil	ASTM D149	372	
Dielectric Constant, 1 kHz	ASTM D150	2.76	
Dissipation Factor, 1 kHz	ASTM D495	0.003	
Dry Arc Resistance, Seconds	ASTM D495	122	
Volume Resistivity, Ohm-cm	ASTM D257	10^14	





PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
THERMAL			
Temperature Range, °C (°F)	Internal	-55 to +200 (-67 to +392)	
Thermal Conductivity, W/m °K	ASTM D518	0.19	
Low Temperature Brittleness	ASTM D2137 -62°C (-80°F) / 3 min	Pass	

Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
0.254	± 0.051
(0.010)	(± 0.002)
0.508	+ 0.076/- 0.051
(0.020)	(+ 0.003/- 0.002)
0.787	± 0.102
(0.031)	(± 0.004)
1.600	± 0.152
(0.063)	(± 0.006)
3.175	± 0.203
(0.125)	(± 0.008)

Width Tolerances

NOMINAL WIDTH	TOLERANCE	
mm (inches)	mm (inches)	
914 (36)	+ 25.4/- 0 (+ 1/- 0)	

Notes:

Additional industry specifications are available as well. All other properties are based on industry standard guidelines.

All metric conversions are approximate. Reference US customary units for official values and tolerances.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO logo, and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2002, 2003, 2004, 2018, 2019, 2020 Rogers Corporation.

All rights reserved. 0320-PDF • Publication #180-090

^{*}Typical Value- Value is based on historical data. Please note the frequency of testing varies.

^{**}Specification- Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values.