

TBP Converting, Inc. 3M 5906, 5907, 5908, 5909 PDS

3M VHB[™] Thin Foam Tape 5906, 5907, 5908, 5909

Product Description	with pressure sensitive adhesive on be range of materials, including many pa to metals and other plastics. The foam	6, 5907, 5908 and 5909 are thin foam tapes oth sides and are used for bonding a wide ints and lower surface energy plastics in addition is conformable to increase contact with the products in the 3M TM VHB TM Tape 5952
Product Construction	Adhesive:	Modified Acrylic
	Thickness: 5906 5907 5908 5909	0.006 in (0.15 mm) 0.008 in (0.20 mm) 0.010 in (0.25 mm) 0.012 in (0.3 mm)
	Thickness Tolerance:	+/- 15%
	Density:	45 lb/ft ³ (720 kg/m ³)
	Liner:	0.003 in (0.08 mm) clear polyester
	Tape Color:	Black
Properties and	Note: The following technical informati or typical only and should not be	on and data should be considered representative
Properties and Performance	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C	ion and data should be considered representative used for specification purposes. 10 lb/inch (175 N/100 mm) 10 lb/inch (175 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 1000 g/0.5 sq in (holds 10,000 min.)
Properties and Performance	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C (stainless steel) 70°C	ion and data should be considered representative used for specification purposes. 10 lb/inch (175 N/100 mm) 10 lb/inch (175 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 1000 g/0.5 sq in (holds 10,000 min.) 500 g/0.5 sq in (holds 10,000 min.)
Typical Physical Properties and Performance Characteristics	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C	ion and data should be considered representative used for specification purposes. 10 lb/inch (175 N/100 mm) 10 lb/inch (175 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 1000 g/0.5 sq in (holds 10,000 min.)
Properties and Performance	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C (stainless steel) 70°C Solvent Resistance: Temperature Resistance: Short Term: (minutes, hours)	ion and data should be considered representative used for specification purposes. 10 lb/inch (175 N/100 mm) 10 lb/inch (175 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 1000 g/0.5 sq in (holds 10,000 min.) 500 g/0.5 sq in (holds 10,000 min.) High 121°C (250°F)
Properties and Performance Characteristics	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C (stainless steel) 70°C Solvent Resistance: Temperature Resistance: Short Term: (minutes, hours) Long Term: (days, weeks)	ion and data should be considered representative used for specification purposes. 10 lb/inch (175 N/100 mm) 10 lb/inch (175 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 1000 g/0.5 sq in (holds 10,000 min.) 500 g/0.5 sq in (holds 10,000 min.) High 121°C (250°F) 82°C (180°F)
Properties and Performance Characteristics	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C (stainless steel) 70°C Solvent Resistance: Temperature Resistance: Short Term: (minutes, hours) Long Term: (days, weeks) Standard Length: 1 inch (25.4 mm) to 8 inch (203 mm)	ion and data should be considered representative used for specification purposes. 10 lb/inch (175 N/100 mm) 10 lb/inch (175 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 1000 g/0.5 sq in (holds 10,000 min.) 500 g/0.5 sq in (holds 10,000 min.) High 121°C (250°F) 82°C (180°F) 65.8 meters (72 yards) 329 meters (360 yards)
Properties and Performance Characteristics	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C (stainless steel) 70°C Solvent Resistance: Temperature Resistance: Short Term: (minutes, hours) Long Term: (days, weeks) Standard Length: 1 inch (25.4 mm) to 8 inch (203 mm) All other	ion and data should be considered representative used for specification purposes. 10 lb/inch (175 N/100 mm) 10 lb/inch (175 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 10 lb/inch (210 N/100 mm) 12 lb/inch (210 N/100 mm) 1000 g/0.5 sq in (holds 10,000 min.) 500 g/0.5 sq in (holds 10,000 min.) High 121°C (250°F) 82°C (180°F) 65.8 meters (72 yards) 329 meters (360 yards) 165 meters (180 yards)
Properties and Performance Characteristics	or typical only and should not be Peel Adhesion: 5906 (stainless steel) 5907 5908 5909 Static Shear: 22°C (stainless steel) 70°C Solvent Resistance: Temperature Resistance: Short Term: (minutes, hours) Long Term: (days, weeks) Standard Length: 1 inch (25.4 mm) to 8 inch (203 mm) All other Minimum Width:	In the second

TBP Converting, Inc. 400 Thoms Drive Suite 411, Phoenixville, PA 19460 Toll: 800-850-3338 Fax: 610-933-4710 www.tbpconverting.com

3M[™] VHB[™] Thin Foam Tape 5906, 5907, 5908, 5909

For maximum bond strength the surfaces should be thoroughly cleaned with a 50:50 mixture of isopropyl alcohol and water. Consult manufacturers directions for use and precautions when using cleaning solvents. Ideal tape application is accomplished when temperature is between 21°C and 38°C (between 70°F and 100°F) and the bond is allowed to dwell 72 hours. Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended.	
24 Months from date of shipment when stored at 4°C to 38°C (40°F to 100°F) and 0-95% relative humidity. The optimum storage conditions are 22°C (72°F) and 50% relative humidity.	
The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.	
Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.	
3M warrants for 24 months from the date of shipment that 3M [™] VHB [™] Tape will be free of defects in material and manufacture. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. This limited warranty does not cover damage resulting from the use or inability to use 3M [™] VHB [™] Tape due to misuse, workmanship in application, or application or storage not in accordance with 3M recommended procedures. AN APPLICATION WARRANTY EXPRESSLY APPROVED AND ISSUED BY 3M IS AN EXCEPTION. THE CUSTOMER MUST APPLY FOR A SPECIFIC APPLICATION WARRANTY AND MEET ALL WARRANTY AND PROCESS REQUIREMENTS TO OBTAIN AN APPLICATION WARRANTY. CONTACT 3M FOR MORE INFORMATION ON APPLICATION WARRANTY TERMS AND CONDITIONS.	
If the 3M [™] VHB [™] Tape is proved to be defective within the warranty period stated above. THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M [™] VHB [™] TAPE. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including negligence, warranty, or strict liability.	