

TBP Converting, Inc. Sika 1A PDS Product Data Sheet Edition 9.13.2012 Sikaflex-1a

## Sikaflex®-1a

## One part polyurethane, elastomeric sealant/adhesive



Description	Sikaflex-1a is a premium-grade, high-performance, moisture-cured, 1-component, polyurethane-based, non-sag elastomeric sealant. Meets Federal specification TT-S-00230C, Type II, Class A. Meets ASTM C-920, Type S, Grade NS, Class 35, use T, NT, O, M, G, I; Canadian standard CAN/CGSB 19.13-M87.				
Where to Use	<ul> <li>Designed for all types of joints where maximum depth of sealant will not exceed 1/2 in.</li> <li>Excellent for small joints and fillets, windows, door frames, reglets, flashing, common roofing detail applications, and many construction adhesive applications.</li> <li>Suitable for vertical and horizontal joints; readily placeable at 40°F.</li> <li>Has many applications as an elastic adhesive between materials with dissimilar coefficients of expansion.</li> <li>Submerged conditions, such as canal and reservoir joints.</li> </ul>				
Advantages	<ul> <li>Eliminates time, effort, and equipment for mixing, filling cartridges, pre-heating or thawing, and cleaning of equipment.</li> <li>Fast tack-free and final cure times.</li> <li>High elasticity - cures to a tough, durable, flexible consistency with exceptional cut and tear-resistance.</li> <li>Stress relaxation.</li> <li>Excellent adhesion - bonds to most construction materials without a primer.</li> <li>Excellent resistance to aging, weathering.</li> <li>Proven in tough climates around the world.</li> <li>Odorless, non-staining.</li> <li>Jet fuel resistant.</li> <li>Certified to the NSF/ANSI Standard 61 for potable water.</li> <li>Urethane-based; suggested by EPA for radon reduction.</li> <li>Paintable with water-, oil- and rubber-based paints.</li> <li>Capable of ±35% joint movement.</li> </ul>				
Coverage	10.1 fl. oz. cartridge seals 12.4 lineal ft. of $1/2 \times 1/4$ in. joint. 20 fl. oz. uni-pac sausage seals 24 lineal ft. of $1/2 \times 1/4$ in. joint.				
Packaging	Disposable 10.1 fl. oz., moisture-proof composite cartridges, 24/case; and uni-pac sausages, 20 fl. oz., 20/carton.				

## Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life 10.1 fl. oz. cartridges 12 months 20 fl. oz. uni-pac sausages 12 months

5 gallon pail 6 months 55 gallon drum 6 months

**Storage Conditions** Store at 40°-95°F (4°-35°C). Condition material to 65°-75°F before using.

Colors White, colonial white, aluminum gray, limestone, black, dark bronze, capitol tan,

stone and medium bronze. Special architectural colors on request.

**Application Temperature** 40° to 100°F. Sealant should be installed when joint is at mid-range of its anticipated movement.

Service Range -40° to 170°F

Curing Rate Tack-free time 3 to 6 hours

Tack-free to touch 3 hours Final cure 4 to 7 days

 Tear Strength (ASTM D-624)
 55 lb./in.

 Shore A Hardness (ASTM C-661)
 21 day 40±5

Movement Capability (ASTM C-719) +/- 35%

**Tensile Properties (ASTM D-412)** 

21 day Tensile Stress 175 psi (1.21 MPa)

Elongation at Break 550%

Modulus of Elasticity 25% 35 psi (0.24 MPa) 50% 60 psi (0.41 MPa) 100% 85 psi (0.59 MPa)

Adhesion in Peel (TT-S-00230C, ASTM C 794)

Substrate Peel Strength Adhesion Loss

 Concrete
 20 lb.
 0%

 Aluminum
 20 lb.
 0%


 Glass
 20 lb.
 0%

Weathering Resistance Excellen

**Chemical Resistance** Good resistance to water, diluted acids, and diluted alkalines. Consult Technical Service for specific data.



How to Use Surface Preparation	dry, frost-free, and free of oil and grease. Curing compound residues and any other foreign matter must		Linear Feet of Sealant per Gallon  Depth			
			Inches	1/4	·	
	be thoroughly removed. A roughened surface will also enhance bond. Install bond breaker tape or backer rod		1/4	308.0		
Delevies or	to prevent bond at base of joint.	_	1/2	154.0	77.0	
Priming	Priming is not usually necessary. Most substrates only require priming if testing indicates a need or where sealant will be subjected to water immersion after cure.	3/4	102.7	51.3		
	ant will be subjected to water immersion after cure.  Consult Sikaflex Primer Technical Data Sheet or Techni-	-	1	77.0	38.5	
	cal Service for additional information on priming.		1 ½	61.6	30.8	
Application	Recommended application temperatures: 40°-100°F. For cold weather application, condition units at approximately 70°F; remove prior to using.		1 ¾	51.3	25.7	
	For best performance, Sikaflex-1a should be gunned into joint when joint slot is at mid-point of its designed expansion and contraction.					
	Place nozzle of gun into bottom of the joint and fill entire joint. Keep the nozzle in the sealant, continue on with a steady flow of sealant preceding the nozzle to avoid air entrapment.  Avoid overlapping of sealant to eliminate entrapment of air. Tool sealant to ensure full contact with joint walls and remove air entrapment. Joint dimension should allow for 1/4 inch minimum and 1/2 inch maximum thick ness for sealant. Proper design is 2:1 width to depth ratio,  For use in horizontal joints in traffic areas, the absolute minimum depth of the sealant is 1/2 in. and closed cell backer rod is recommended.					
Limitations	<ul> <li>Allow 1-week cure at standard conditions when using sprior to painting.</li> <li>When overcoating with water, oil and rubber based pail</li> <li>Avoid exposure to high levels of chlorine. (Maximum of Maximum depth of sealant must not exceed 1/2 in.; mil</li> <li>Maximum expansion and contraction should not exceed</li> <li>Do not cure in the presence of curing silicone sealants.</li> <li>Avoid contact with alcohol and other solvent cleaners of Do not apply when moisture-vapor-transmission conditionabling within the sealant.</li> <li>Use opened cartridges and uni-pac sausages the sam When applying sealant, avoid air-entrapment.</li> <li>Since system is moisture-cured, permit sufficient exposionable with the color tends to yellow slightly when exposed to ull Light colors can yellow if exposed to direct gas fired he The ultimate performance of Sikaflex-1a depends on gurfaces properly prepared.</li> <li>The depth of sealant in horizontal joints subject to traff</li> <li>Do not use in contact with bituminous/asphaltic materia</li> </ul>	ints, ontin nimued 25 durin tion e dar sure eltravi eating good iic is als.	compatibility and uous level is 5 pum depth is 1/4 in which will be some for a comparison of the second of the sec	d adhesion test on of chlorine int width. ubstrate as this	ing is essentia .) s can cause ition with joint	
Caution	WARNING: IRRITANT, SENSITIZER. Contains Polyisocyanate Prepolymer (Mixture), Xylene (CAS 1330-20-7). Causes eye irritation. May cause skin/respiratory irritation. May cause skin and/or respiratory sensitization after prolonged contact. May be harmful if swallowed. Reports have associated repeated and prolonged exposure to some of the chemicals in this product with permanent brain, liver, kidney and nervous system damage. Headaches and dizziness may result. Deliberate misuse by inhalation of vapors may be harmful or fatal. Strictly follow all usage, handling and storage instructions.					
Handling & Storage	to prevent direct contact with skin and eyes. Use only i	e equipment (chemical resistant goggles/gloves/clothing) lse only in well ventilated areas. Open doors and windows rator if ventilation is poor. Wash thoroughly with soap and g and launder before reuse. Store in cool dry well				
Cleanup	Use personal protective equipment (chemical resistant gloves/goggles/clothing). Without direct contact, remove spilled or excess product and placed in suitable sealed container. Dispose of excess product and container in accordance with applicable environmental regulations.					



**Eyes:** Hold eyelids apart and flush thoroughly with water for 15 minutes. **Skin**: Remove contaminated clothing. Wash skin thoroughly for 15 minutes with soap and water. **Inhalation:** Remove to fresh air. **Ingestion:** Do not induce vomiting. Dilute with water. Contact physician. **In all cases contact a** 

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available online at <a href="https://www.sikausa.com">www.sikausa.com</a> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use.

LIMITED WARRANTY: Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor NOOTHERWARRANTIES EXPRESS OR IMPLIED SHALLAPPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR APARTICULAR PURPOSE. SIKASHALLNOTBELIABLEUNDERANYLEGALTHEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKASHALLNOTBERESPONSIBLE FOR THE USE OF THIS PRODUCT INAMANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.



**First Aid Measures** 

container in accordance with applicable environmental regulations.

physician immediately if symptoms persist.