



TBP Converting, Inc.
Rogers Poron 4701-15 PDS

PORON® 4701-15 Soft Seal Series
Enhanced Surface Toughness, Reliable Materials for Thinner Designs

PROPERTY	TEST METHOD	VALUE		
PHYSICAL				
Density, kg / m ³ (lb / ft ³)	ASTM D 3574-95, Test A	104 (6.5)		
Tolerance, kg / m ³ (lb / ft ³)		16 (±1)		
Thickness, mm (inches)		0.53 (0.021)	0.75 (0.030)	1.00 (0.039)
Tolerance, mm (inches)		0.10 (± 0.004)		
Compression Force Deflection, Typical value, kPa (psi)	.51 cm/min (0.2" / min) Strain Rate Force Measured @ 25% Deflection	2.00 (0.29)	2.41 (0.35)	4.62 (0.67)
Compression Set, % max.	ASTM D 3574-95 Test D @ 70°C (158°F)	10		
Standard Color (Code)		Gray (90)		
Thermal Conductivity, W/mK	Rogers Internal (Typical Value)	0.06		

With the exception of the thickness measurement, the data mentioned above represents results of testing the PORON polyurethane foam only. This product is supported on a 2-mil (0.05mm) polyester film (PET) creating a permanent bond. Please see physical property data for the film as represented by the manufacturer below.

Supporting Material - Clear Polyester Film (PET)

PROPERTY	TEST METHOD	VALUE
Coefficient of Friction A/B, (Kinetic)	ASTM D 1894	0.40
Density, kg/m ³ (lb / ft ³)	ASTM D 1505	1395 (87.1)
Modules, MD, kPa (psi)	ASTM D 882	3.5 x 10 ⁶ (500,000)
Shrinkage, MD, %, (TD)	39 min. at 150°C (302°F)	1.2 (0.0)
Tensile Strength, MD, kPa (psi)	ASTM D 882	2.1 x 10 ⁵ (30,000)
Ultimate Elongation, %	ASTM D 882	150
Yield Strength (F5), kPa (psi)	ASTM D 882	1.0 x 10 ⁵ (15,000)

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Typical values should not be used for specification limits.

The information contained in this data sheet is intended to assist you in designing with Rogers' PORON Polyurethane Materials. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers' PORON Materials for each application. The Rogers logo, Helping power, protect, connect our world and PORON are trademarks of Rogers Corporation or one of its subsidiaries. © 2009, 2016 Rogers Corporation, All rights reserved. Printed in U.S.A., 0416-PDF, Publication #17-203