



Technical Data Sheet

3M™ Industrial Adhesive 4475



Product Details



Regulatory Info/SDS

Product Features

- Dries quickly to a firm bond.
- Excellent resistance to water, plasticizer migration, many detergent and soap solutions, oils and grease.
- A general purpose adhesive for bonding most vinyls, ceramics, glass, leather and cloth to a variety of substrates.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Attribute Name	Value
Net Weight	8.3 lb/gal
Base	Synthetic Resin

Typical Physical Properties

Attribute Name	Temperature	Value
Color		Clear
Solids Content by Weight		41 to 45 %
Carrier Solvent		methyl ethyl ketone (MEK)
Coverage		487 ft ² /gal ¹
Flash Point		20 °F ²
Viscosity	27 °C (80 °F)	6,500-10,500 cP ³

¹ 1 mil dry film

² Closed Cup

³ Brookfield Viscometer RVF #5 sp. @ 20 rpm

Typical Performance Characteristics

180° Peel Adhesion

Substrate: Canvas to Steel

Dwell Time	Temperature	Value
24 h	22 °C (72 °F)	208 oz/in
72 h	22 °C (72 °F)	384 oz/in
120 h	22 °C (72 °F)	440 oz/in
168 h	22 °C (72 °F)	520 oz/in
2 week	22 °C (72 °F)	560 oz/in
3 week	22 °C (72 °F)	704 oz/in
3 week	-34 °C (-29 °F)	352 oz/in
3 week	66 °C (150 °F)	272 oz/in
3 week	82 °C (180 °F)	112 oz/in

Handling/Application Information

Directions for Use

1. Surface Preparation: Best results are achieved on clean, dry surfaces. Oil, grease and other contaminants can be removed by wiping with a solvent such as methyl ethyl ketone (MEK).*
2. Application: Apply adhesive to one or both surfaces (best results are obtained by coating both surfaces) and bond immediately using firm pressure.
3. Drying Time: Allow to dry a minimum of 24 hours for maximum strength.
4. Cleanup: Remove unhardened or hardened material with cloth dampened with a solvent such as methyl ethyl ketone (MEK).*

*Note: When using solvents, extinguish all ignition sources and follow the manufacturer's precautions and directions for use.

Application Equipment

Note: Appropriate application equipment can enhance adhesive performance. The user is responsible for evaluating application equipment in light of the user's particular purpose and method of application.

1. Pumping

5-Gallon Pail Dispensing System

Pump - 9:1 ratio double acting ball check type pump, 11.0 cubic inches per cycle, 41/4" diameter air motor minimum. Pail cover to be used to reduce solvent loss.

55-Gallon Drum Dispensing System

Pump - 10:1 ratio double acting ball check type pump, 11.0 cubic inches per cycle, 41/4" diameter air motor minimum, Bung mount type.

2. Accessories

Hose - 1000 psi minimum working pressure, nylon lined. Flow rate at 40°F, 20 ft. of 3/4-ID plus 10 ft. 1/2-ID and a flow gun equals 1 pound/minute at pump air pressure of 75 psi.

3. Chemical Resistance Requirements

Synthetic materials in contact with this product must be resistant to ketones and aromatic solvents. Compare, nylon or PTFE coatings are suggested for packings and gaskets.

Storage and Shelf Life

Best storage temperature is 60-80°F (16-27°C). Higher temperatures reduce normal storage life. Lower temperatures cause increased viscosity of a temporary nature. Rotate stock on a "first in, first out" basis.

When stored at the recommended temperature in the original, unopened container, this product has a shelf life of 30 months from date of manufacture.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Automotive Disclaimer

Select Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M is a trademark of 3M Company.
©3M 2022 (6/22)