

## PORON® SlimGrip Plus 4701-SG+RL

PORON® SlimGrip Plus is the softest PORON material to date with increased cohesive strength for ease of processing. The high level of compressibility and superior compression set resistance proves PORON SlimGrip Plus ideal for sealing applications with low compression set requirements.

PROPERTY	TEST METHOD	VA	VALUE	
PHYSICAL		SG+RL-06014	SG+RL-06020	
Density, kg/m³ (lb./ft³)	ASTM D 3574-95, Test A	104 (6.5)	104 (6.5)	
Tolerance		± 16 (1)	± 16 (1)	
Thickness, mm (inches)	Digital Tester (ONO SOKKI)	0.35 (0.014)	0.51 (0.020)	
Tolerance, %		+15/-20	± 20	
Standard Color (Code)		Gray (90)	Gray (90)	
Cohesion (gf/25mm), Typical		> 100	> 100	
Compression Force Deflection, kPa (psi)	Modified ASTM D 3574 PTP-0033 @ 25% deflection	1.38 - 5.85	1.38 - 5.85	
		0.2 - 0.85	0.2 - 0.85	
Compression Set, % max	ASTM D 3574-95 Test D @ 70°C (158°F)	10	10	

<sup>\*</sup>The data above is the result of testing only PORON polyurethane. The product is directly cast onto a removable 0.05mm (2mil) polyester film (PET).

## Notes:

- All metric conversions are approximate.
- Additional technical information and product specifications are available upon request.
- Typical values should not be used for specification limits.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of PORON Polyurethane Foam Materials for each application. The Rogers logo, PORON, and the PORON logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2019, 2020 Rogers Corporation.

All rights reserved. 0720-PDF • Publication #17-426

