



# Technical Data Sheet

## 3M™ Marine Adhesive/Sealant Fast Cure 4000 UV



Product Details



Regulatory Info/SDS

### Product Description

3M™ Marine Adhesive/Sealant 4000 UV is a one-part adhesive sealant that cures to form a firm, rubbery waterproof seal. Its flexibility allows for the dissipation of stress caused by shock, vibration, swelling or shrinking. Designed for marine applications above and below the waterline. Its superior UV resistance properties makes this an ideal cosmetic adhesive sealant.

### Product Features

- Superior UV resistance.
- Exceptional sealing properties.
- <1% VOC's
- Low odor.
- Non-shrinking.
- Non-sagging.
- Non-corrosive.
- Non-cracking.
- Caulkable at low temperatures (>40°F [4°C]).
- Fast curing.
- Paintable (test for suitability).

### Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

### Typical Uncured Physical Properties

Attribute Name	Value
Density	11.7 lb/gal
Consistency	Medium Paste
Base	Polyether

### Typical Physical Properties

Attribute Name	Value
Color	White Black
Product Construction	10 fl. oz. cartridge (295 ml) 3 fl. oz. tube (90 ml) 400 ml Flex Pack (13.5 fl. oz.)
Approximate Coverage	36.6 lineal m (120 LF) <sup>1</sup>

<sup>1</sup> 10.5 oz. [310 mm Cartridge]; 1/8 in (3 mm) bead

## Typical Cured Characteristics

Attribute Name	Test Method	Value
Shore A Hardness	ASTM C661	39

## Typical Performance Characteristics

### 180° Peel Adhesion

Temperature: 23 °C (73 °F)

Substrate	Value
Aluminum	70 oz/in (Cohesive) <sup>1</sup>
Fiberglass	57 oz/in (Cohesive) <sup>1</sup>
Gelcoat	60 oz/in (Cohesive) <sup>1</sup>
Mahogany	50 oz/in (Cohesive) <sup>1</sup>

<sup>1</sup> 25 mm (1 in) wide specimens on canvas.

Cohesive - Adhesive/Sealant fails before adhesive/sealant releases from substrate. This is the desired mode.

Adhesive Failure - Adhesive/Sealant releases from substrate.

### Overlap Shear Strength

Temperature: 23 °C (73 °F)

Substrate	Value
Oak	13.385/15 kg/cm <sup>2</sup> (19085/15 lb/in <sup>2</sup> ) (Cohesive/Adhesive) <sup>1</sup>
Maple	14.880/20 kg/cm <sup>2</sup> (21080/20 lb/in <sup>2</sup> ) (Cohesive/Adhesive) <sup>1</sup>
Fir	13.370/30 kg/cm <sup>2</sup> (19070/30 lb/in <sup>2</sup> ) (Cohesive/Adhesive) <sup>1</sup>
Mahogany	11.260/40 kg/cm <sup>2</sup> (16060/40 lb/in <sup>2</sup> ) (Cohesive/Adhesive) <sup>1</sup>
Aluminum	15.880/20 kg/cm <sup>2</sup> (22580/20 lb/in <sup>2</sup> ) (Cohesive/Adhesive) <sup>1</sup>
Fiberglass	14.0 kg/cm <sup>2</sup> (200 lb/in <sup>2</sup> ) (Cohesive) <sup>1</sup>
Gelcoat	17.6 kg/cm <sup>2</sup> (250 lb/in <sup>2</sup> ) (Cohesive) <sup>1</sup>

<sup>1</sup> 25 mm (1 in) overlap specimens 2.4 mm (0.093 in) thick.

Cohesive - Adhesive/Sealant fails before adhesive/sealant releases from substrate. Desired failure mode.

Adhesive Failure - Adhesive/Sealant releases from substrate.

Attribute Name	Temperature	Substrate	Value
Application Temperature			4 – 38 °C (40 – 100 °F)
Long Term Temperature Resistance			90 °C (190 °F) <sup>1</sup>
Minimum Long Term Temperature Resistance			-40 °C (-40 °F) <sup>1</sup>
Temperature Resistance	23 °C (73 °F)	Fir	17.655/45 kg/cm <sup>2</sup> (25055/45 lb/in <sup>2</sup> ) (Cohesive/Adhesive) <sup>2</sup>
Temperature Resistance	23 °C (73 °F)	Aluminum	28.195/5 kg/cm <sup>2</sup> (40095/5 lb/in <sup>2</sup> ) (Cohesive/Adhesive) <sup>2</sup>

Attribute Name	Temperature	Substrate	Value
Temperature Resistance	23 °C (73 °F)	Gelcoat	19.3 kg/cm <sup>2</sup> (275 lb/in <sup>2</sup> ) (Cohesive ) <sup>2</sup>
Temperature Resistance	23 °C (73 °F)	Fiberglass	22.880/20 kg/cm <sup>2</sup> (32580/20 lb/in <sup>2</sup> ) (Cohesive/Adhesive ) <sup>2</sup>

<sup>1</sup> Long Term (day, weeks)

<sup>2</sup> 25 mm (1 in) overlap specimens 2.4 mm (0.093 in) thick. Aged 500 hours @ 190 °F (90 °C).  
Cohesive - Adhesive/Sealant fails before adhesive/sealant releases from substrate. Desired failure mode.  
Adhesive Failure - Adhesive/Sealant releases from substrate.

Attribute Name	Temperature	Value
Elongation		>300 % <sup>1</sup>
Tensile Strength	23 °C (73 °F)	28.1 kg/cm <sup>2</sup> (>400 lb/in <sup>2</sup> ) <sup>1</sup>

<sup>1</sup> A 3.2 mm (1/8 in) dumbbell specimen with a 3.2 mm (1/8 in) square cross section was tested at 51 mm/min (2 in/min)

## Product Uses

3M Marine Adhesive Sealant 4000 UV may be used in typical bedding and sealing applications including fiberglass hull, wood to fiberglass, porthole frames, deck fittings, moldings, thru hull and deck hardware.

## Handling/Application Information

### Directions for Use

#### 1. Surface Preparation

Surface should be clean, dry and free of contaminants. New surfaces should be solvent wiped with 3M™ General Purpose Adhesive Cleaner 08984\*, or equivalent. Other than new surfaces should be sanded with a fine grade abrasive to enhance bond strength.

#### 2. Sealing and bedding application

Apply 3M™ Marine Adhesive/Sealant 4000 UV to the seam or part to be bonded. Position parts. Tool and squeeze out material to desired appearance. Remove excess with 3M general purpose adhesive cleaner 08984.\*

#### 3. Cleanup

For cleaning 3M marine adhesive/sealant 4000 UV before it is cured, use a dry cloth to remove the majority, followed by a cloth damp with 3M general purpose adhesive cleaner, toluene, acetone, or other good cleaning solvent.\*  
Cured 3M marine adhesive/sealant 4000 UV can be removed mechanically with a knife, razor blade, piano wire or by sanding.

\*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

### Cure:

Tack Free (50%RH, 22 °C, 72 °F): 22 min

Full Cure (50%RH, 22 °C, 72 °F): 24 hr with 3.2 mm (1/8 in) depth of cure

\*Higher temperature and humidity conditions will accelerate the tack free time and cure. Please plan accordingly.

## Application Examples

### Typical Marine Adhesive Sealant Applications:

Portlights  
Hatches  
Thru-hulls  
Rails  
Metal Hardware  
Moldings  
Wood  
Teak  
Fiberglass  
Gelcoat  
Porthole Frames

## Storage and Shelf Life

Store under normal conditions of 16° to 27°C (60° to 80°F) and 40 to 60% relative humidity in the original packaging, out of direct sunlight. Lower temperatures cause increased viscosity of a temporary nature. When stored at recommended conditions, the shelf life is 15 months from date of manufacture for cartridges and sausage packs. When stored at recommended conditions, the shelf life is 15 months from date of manufacture for 3 ounce tubes.

## Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577

## Automotive Disclaimer

### Select Automotive Applications:

This product is an industrial product and has not been designed or tested for use in certain automotive applications, such as automotive electric powertrain battery or high voltage applications, which may require the product to be manufactured in a IATF certified facility, meet a Ppk of 1.33 for all properties, undergo an automotive production part approval process (PPAP), or fully adhere to automotive design or quality system requirements (e.g., IATF 16949 or VDA 6.3). Customer assumes all responsibility and risk if customer chooses to use this product in these applications.

## Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).

## ISO Statement

This product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M is a trademark of 3M Company.  
© 3M 2024 (9/24)