

Surface Guard[®] PolyMask Protective Film

2A825

Technical Data

February, 2017

Product Description Surface Guard[®] PolyMask Protective Film 2A825 is a co-extruded, medium adhesion protective film designed for a variety of surface protection applications.

Product Construction	Backing	Adhesive	Color	Standard Roll Sizes
	Multi-Polymer	Acrylic-Based	Clear*	Custom

* Contact your local SG PolyMask representative for additional information on colors.

Typical Physical Properties **Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.**

	Nominal Results	ASTM Test Method
Adhesion to Steel:	6 oz./in. width (1.65 N/25 mm)	D-3330**
Tensile:	4500 PSI	D-882**
Elongation:	600%	D-882**
Total Tape Thickness:	2 mils (0.05 mm)	D-3652**

** ASTM test references modified per internal test methods.

Features

- Effective in many outdoor applications for up to 3 days.
- Surface protection against dust, dirt, scratches and abrasion encountered in processing, handling, shipping and storage.
- Stable adhesion levels resulting in good removability.
- SG PolyMask proprietary high performance film with higher abrasion resistance vs. many typical thicker gauge films, offering good clarity, excellent conformability for hand and machine applied applications.
- Increased break strength for easier removability without tearing or slivering.

Application Ideas

- **General** – smooth semi-gloss cultured marble, high pressure laminates.
- **Metals** – 2B #3 and #4 finish stainless steel.
- **Painted** – smooth semi-gloss.
- **Plastics** – smooth semi-gloss.



Surface Guard[®] PolyMask Protective Film

2A825

Application / Removal Techniques	<ul style="list-style-type: none">• For optimum performance, SG PolyMask Protective Films should be applied and removed at a temperature not less than 60°F (16°C).• Surfaces should be dry and free from dirt, oil and other contaminants when film is applied.• Protective film should be removed gradually beginning from one edge with a smooth even motion.
Storage	Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% R.H in the original carton.
Shelf Life	To obtain best performance, use this product within 12 months from date of manufacture.
For Additional Information	To request additional product information or to arrange for sales assistance, call toll free 1-844-232-6783. Address correspondence to: SG PolyMask, 500 Thornburg Dr., Conover, NC 28613.
Technical Information	The technical information, recommendations and other statements contained in this document are based upon tests or experience that SG PolyMask believes are reliable, but the accuracy or completeness of such information is not guaranteed.
Product Use	Many factors beyond SG PolyMask's control and uniquely within user's knowledge and control can affect the use and performance of a SG PolyMask product in a particular application. Given the variety of factors that can affect the use and performance of a SG PolyMask product, user is solely responsible for evaluating the SG PolyMask product and determining whether it is fit for a particular purpose and suitable for user's method of application.
Warranty and Limited Remedy	Unless an additional warranty is specifically stated on the applicable SG PolyMask product packaging or product literature, SG PolyMask warrants that each SG PolyMask product meets the applicable SG PolyMask product specification at the time SG PolyMask ships the product. SG PolyMask MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the SG PolyMask product does not conform to this warranty, then the sole and exclusive remedy is, at SG PolyMask's option, replacement of the SG PolyMask product or refund of the purchase price.
Limitation of Liability	Except where prohibited by law, SG PolyMask will not be liable for any loss or damage arising from the SG PolyMask product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9001